@

EUROPEAN PATENT APPLICATION

Application number: 89300631.2

(a) Int. Ct.4: H 05 H 1/34

Date of filing: 24.01.89

- Priority: 25.01.88 NO 880288
- Date of publication of application: 02.08.89 Bulletin 89/31
- Designated Contracting States:

 AT BE CH DE ES FR GB GR IT LI LU NL SE
- (7) Applicant: ELKEM TECHNOLOGY A/S P.O. Box 4376 Torshov N-0402 Osto 4 (NO)
- (3) Inventor: Elkeland, Inger Johanne Kirkevelen 48 N-0368 Osio 3 (NO)

Poppe, Per Granalisen 17 N-1322 Hovik (NO)

@ Representative: Rees, David Christopher et all Külburn & Strode 30 John Street London WC1N 2DD (GB)

Plasma torch.

A plasma torch intended to be submerged in a bath of moiten metal, such as a steel met. The torch comprises an outer electrode (1) made from a non-consumable material and an inner electrode (1a). The outer electrode (1) is a copper pipe having internal channels for a cooling medium, and having a layer of refractory material (7) on the outside. The layer of refractory material has a thickness between 1 and 5mm and is made from Al2O₂ or from ZrO₂ stabilised with 5-25% by weight of MgO and/or Y₂O₃, or from coddes of other rare earth




Fig. 1

Aundrechuckerel Geran

EP 0 326 318 A2

Description

PLASMA TORCH

The present invention relates to a plasma torch for generating a high temperature plasma by means of an electric arc between a ring-shaped outer electrode and an inner electrode arranged coaxially in the outer electrode. More specifically the present invention relates to a plasma torch of this kind which is intended to be submerged in molten metal such as a bath of molten steel.

Plasma torches which are intended to be submerged in molten metal in which the electrodes are made from a comsumable matelal such as for example graphito are known. These torches, however, have a number of drawbacks and disadvantages. Graphite electrodes quite frequently break, resulting in disruption of the heating of the metal melt. Also, graphite electrodes cannot be used with metal metts in which graphite dissolves, such as steal melts, malts of ferromaganese, etc. Furthermore, the plasma torch has to be equipped with means for feeding of the graphite electrodes as these are consumed; this makes the design of the plasma torch complex. Finally the consumption of the graphite electrode is the main factor which leads to high operating costs for this kind of plasma torch.

It is an object of the present invention to provide a plasma torch for heating a molten metal bath by submerging the torch in the bath, where at least the outer electrode is made from a non-consumable

According to the present invention, a plasma torch is characterised in that the outer electrode is non-consumable and comprises a copper pipe having an internal channel for a cooling medium, and having a layer of refractory material at least on its outside.

According to a preferred embodiment, the layer of refractory material consists of Al₂O₃ or ZrO₂ stabilised with 5-25%, preferably 20% MgO and/or Y₂O₂, or of oxides of other rare earth elements. The layer of refractory material may have a thickness of 1-5mm, preferably 2-4mm and is preferably applied by flame- or plasma spraying.

The inner electrode may consist of a cooled or non-cooled copper pipo or may be of a consumable material, such as graphite. The current supply to the electrodes is preferably arranged in such a way that the arc will rotate about the tip of the outer electrodes.

An alternative embodiment of the present invention includes a pipe made from a ceramic material such as aluminium oxide, on the outside and at a distance from the outer ring-chaped electrode. The pipe is open at its lower end, whereby motiten metal can flow into the annulus between the outer electrode and the ceramic pipe.

An oil or molten metal having a low melting temperature, may be used as the cooling medium for cooling the outer electrode.

The plasme torch according to the present invention can further be equipped with means which makes it possible to supply alloying additions to the

metal melts through the annulus between the innor and the outer electrods.

The thermal insulating layer of refractory material on the outside of the outer electrode has a number of functions. Firstly, the copper pipe is protected against thermal and chemical stress when the torch is submerged in the molten bath. The lifetime of the outer electroda can thereby be substantially increased. Secondly the layer on the outer electrode acts as a thermal barrier between the motion motel and the copper pipe, whereby heat which is removed from the melt by the internal cooling of the copper pipe is substantially reduced. Thus, the thermal efficiency of the torch is increased. In the case of the plasma torch with an outer electrode comprising a cooled copper pipe without an outer layer, the heat loss from the metal bath through the coppor pipe and through the cooling medium would be substantial and would reduce the thermal efficiency of the plasma torch.

in operation a gas is prefembly supplied to the annulus between the outer and the inner electrodes and the electric are to struck between the electrode tips. The inside of the outer electrode and the inner electrode may be coaled by the gas which is supplied to the annulus and it would therefore not normally be necessary to have a layer of refrectory material on these parts.

By arranging a commic tube on the outside of, and at a distance from, the outer ring-shaped electrode, increased protection of the plasma torch may be obtained. When a plasma torch equipped with such a ceranic tube is submerged into a metal bath, malten metal will flow into the annulus between the cutor electrode and the ceranic tube. The motion metal in this annulus will be more or base at rest and will tend to protect the outer electrode.

The invention may be certical into practice in various ways and two embediments will now be described by way of example with reference to the accompanying drawings, in which:

Figure 1 is a vertical section through a phasma torch according to the present invention, and Figure 2 is a similar view showing a cocond

Figure 2 to a similar view showing a second embediment in which the outer electrode is surrounded by a caremic tube.

The pleams torch shown in Figure 1 comprises an outer electrode 1 and an inner electrode 1a. The outer electrode 1 consists of a ring-shaped copper pipe having an inner wall 2 and an outer wall 3. The copper pipe is equipped with an internal wall 4 which extends downwards from the top of the pipe and stope above the bottom of the copper pipe. The copper pipe is further equipped with an internal copping 5 and an outlat opening 6 for a liquid cooling medium.

The copper pipe has on its outer wall 3 a layer 7 of refractory material. The layer of refractory material preferably has a thickness of 1-5mm and is made from Al₂O₃ or from ZrO₂ stabilised with 5-25% MgO and/or Y₂O₃ and is made by flame- or plasma

10

15

spraying. On the lower end of the copper pipe there are preferably inserts made from Wolfram (tungsten), graphite or some other high-temperature resistant material having a low electrical resistivity. Due to the electric arc produced, the inserts on the lower end of the copper pipe will be worn and will have to be replaced from time to time.

The plasma torch has a conventional means for the supply of electric current to the torch (not shown) and is equipped with means for the supply of a gas, such as for example, argon to the annulus between the inner and the outer electrodes.

Figure 2 shows a second embodiment of a plasma torch according to the present invention. In this case, the plasma torch is similar to the embodiment of Figure 1 except hat it is equipped with a ceramic tube 8 located around and spaced from the outer ring-shaped electrode. The tube 8 is open at its lower end and is fixed to the outside of the outer electrode. The length of the ceramic tube 8 is such that the tube extends upwards to a level which is at least above the top of the metal bath when the plasma torch is submerged in the bath,

When the plasma torch is submerged in a metal bath, molten metal will fill the annulus between the outer electrode 1 and the ceramic tube 8. As long as the torch is submerged, the metal in the annulus between the outer electrode 1 and the ceramic tube will more or less be at rest. This part of the molten metal will thus protect the outside of the outer electrode against continuous flow of holt molten metal near the outside of the outer electrode. The heat stress on the layer of refractory material and on the copper pipe will thereby be reduced and the life-time of the plasma torch will be increased.

Claims

1. A plasma torch for generating a high -temperature plasma by means of an electric arc struck between an outer ring-shaped electrode (1) and an inner electrode (1a) coxially located within the outer electrode (1), characterised in that the outer electrode (1) is non-consumable and comprises a copper pipe having internal channel for a cooling medium, and having a layer (7) of refractory material at least on its outside.

2. A plasma torch as cialmed in Claim 1 characterised in that the layer (7) of refractory material has a thickness between 1 and 5mm, preferably between 2 and 4mm.

3. A plasma torch as claimed in Claim 1 or Claim 2 characterised in that the layer of refractory material consists of ZrO2 stabilised with 5-25% preferably 20% MgO and/or Y2O2. or of oxides of other rare earth elements.

4. A plasma torch as claimed in any preceding claim characterised in that the refractory layer (7) is applied by flame- or plasma spraying.

5. A plasma torch as claimed in Claim 1 or Claim 2 characterised in that the refractory layer (7) consists of AlgO₃ which has been applied by flame- or plasma spraying.

6. A plasma torch as claimed in any preceding claim, characterised by a sieeve or tube (8) made from a ceramic material arranged outside and spaced from the outer electrode (1),

7. A plasma torch as claimed in Claim 5, characterised in that the ceramic tube (8) is made from aluminium coide.

8. A plasma torch as claimed in any preceding claim characterised in that the inner electrods (1a) is made from graphite or from copper having internal channels for the circulation of a cooling medium.




Fig. 1




Fig. 2